

# TRIS TUBE CO., LTD.

21, SeungJun-Ro, DongDuCheon, GyeongGi-Prov., Korea 483-110 Tel: 82-31-866-4602 Fax: 82-31-866-5156

URL: http://www.tristube.com/eng

# **TECHNICAL DATA SHEET**

**NICKEL ALLOY** 

**ALLOY C22** 

(UNS N06022)

### □ Application

Alloy C22, is a versatile austenitic nickel-chromiummolybdenumtungsten alloy with enhanced resistance to pitting, crevice corrosion and stress corrosion cracking. The high chromium content provides good resistance to oxidizing

media while the molybdenum and tungsten content give good resistance to reducing media. This nickel alloy also has excellent resistance to oxidizing aqueous media including wet chlorine and mixtures containing nitric acid or oxidizing acids with chlorine ions.

Alloy C22 has resistance to oxidizing acid chlorides, wet chlorine, formic and acetic acids, ferric and cupric chlorides, sea water, brine and many mixed or contaminated chemical solutions, both organic and inorganic. This nickel alloy also offers optimum resistance to environments where reducing and oxidizing conditions are encountered in process streams. This is beneficial in multi-purpose plants where such "upset" conditions occur frequently.

#### **Available tube product forms**

STRAIGHT COILED SEAMLESS

Typical manufacturing specifications

**ASTM B622** 

Also individual customer specifications.

#### Industries predominantly using this grade

Chemical processes, Oil and gas etc.

Maximum Coil Length per Dimension (Unit : meter)									
		Wall thickness (mm)							
		0.51	0.71	0.89	1.24	1.65	2.11		
Outside diamete r (mm)	3.175	-	-	-	-	-	-		
	6.35	-	425	350	268	219	-		
	9.53	-	-	221	166	131	109		
	12.7	-	-	162	120	93	76		
	19.05	-	-	-	77	59	48		
	25.4	-	-	-	57	43	35		


an provide longer length according to customer requirement

## **⊢** Technical Data

Chemical composition(% by weight)												
Element	Cr	Мо	Fe	W	С	Si	Co	Mn	V	Р	S	-
Minimun	20.0	12.5	2.0	2.5	-	-	-	-	-	-	-	-
Maximum	22.5	14.5	6.0	3.5	0.015	0.08	2.50	0.50	0.35	0.02	0.02	-
Aiming	21.0	13.5	3.8	2.8	0.004	0.04	0.001	0.10	0.01	0.001	0.001	-

Mechanical Properties									
	Specifications(Tubing,	Annealed)	Actual data						
Tensile Rm	100	ksi (min.)	108~130	ksi (min.)					
Tensile Rm	690	MPa (min.)	750~900	MPa (min.)					
Yield (R.p. 0.2%)	45	ksi (min.)	50~72	ksi (min.)					
Yield (R.p. 0.2%)	310	MPa (min.)	350~500	MPa (min.)					
Elongation	45	% (min.)	50~60	% (min.)					

Physical Properties(Room Temperature)							
Specific Heat (0-100°C)	414	J.kg-1.°K-1					
Thermal Conductivity	10.2	W.m -1.°K-1					
Thermal Expansion	6.9	mm/m/°C					
Modulus Elasticity	206	GPa					
Electrical Resistivity	4.48	µohm∙cm					
Density	8.69	g/cm3					



Maximum allowable pressure (Unit : BAR)									
		Wall thickness (mm)							
		0.89	1.24	1.65	2.18	2.77	3.96	4.78	
Outside diamete r (mm)	6.35	580	844	1155	1542				
	9.53	373	535	736	1005	1302			
	12.7	275	391	534	729	954			
	19.05		254	344	464	605			
	25.4		188	254	341	441	654	810	
	31.8			201	268	346	509	628	
	38.1			166	222	286	418	513	
	50.8			124	165	211	307	376	

<sup>\*</sup> We follow customer requested dimensions.

<sup>\*</sup> Select tubes according to design pressure

<sup>\*</sup>Disclaimer: The information contained within this data sheet is for guidance only and is not intended for warranty of individual application – express or implied.